



(19)

Generated Document.

(11) Publication number: **05021378 A**

PATENT ABSTRACTS OF JAPAN

(21) Application number: **03202931**

(51) Int. Cl.: **H01L 21/28 H01L 21/205 H01L 21/225**

H01L 21/28 H01L 21/82 H01L 21/3205

H01L 27/04 H01L 21/331 H01L 29/73

H01L 21/336 H01L 29/784

(22) Application date: **13.08.91**

(30) Priority: **31.08.90 JP 02228124**

(43) Date of application publication: **29.01.93**

(84) Designated contracting states:

(71) Applicant: **HITACHI LTD**

(72) Inventor: **KOBAYASHI TAKASHI**

IJIMA SHINPEI

HIRAIWA ATSUSHI

KOBAYASHI NOBUYOSHI

NANBA MITSUO

HASHIMOTO KOJI

(74) Representative:

(54) MANUFACTURE OF SEMICONDUCTOR DEVICE

(57) Abstract:

PURPOSE: To provide a method of manufacturing a silicon film including boron which ensures excellent step-portion covering characteristic and is just suitable for

manufacturing process under a low temperature condition.

CONSTITUTION: An amorphous Si film is deposited by the pressure-reduced CVD method under a low temperature of 200 or higher and 400°C or lower using any one of disilane (Si_2H_6) or trisilane (Si_3H_8) and dibolane (B_2H_6). Thereby, a Si film including boron which ensures excellent step-portion covering characteristic can be formed. Using the obtained Si film as a diffusion source, extremely shallow junction may be formed.

COPYRIGHT: (C)1993,JPO&Japio



